



TEXAS - LEHIGH CEMENT COMPANY

P.O. Box 610 Buda, Texas 78610 (512) 295-6111

LABORATORY TEST REPORT

AASHTO Accredited

Consignee: _____ Address _____

Date _____ Plant _____

Type N - Masonry Car/Truck _____ Bin No. _____ Quantity _____

RESULT OF TESTS

Remarks _____	-325 sieve(ASTM C 430) _____ 96
_____	Autoclave Exp.(%)-ASTM C151) _ 0.0
_____	Time of Set(Gillmore)-ASTM C266
_____	Initial (Minutes) _____ 180
_____	Final (Minutes) _____ 345
_____	Air Content(%)-ASTM C185 _____ 15
_____	H2O Retention(ASTM C 91) _____ 84
_____	Compressive Strength, psi (ASTM C109 Mortar Cubes):
_____	7 - Day _____ 1930
_____	28 - Day _____ 2300

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of the current applicable specification ASTM C91. The above data represents the average of representative samples from production. We are not responsible for improper use or workmanship.

Date: May 23, 2002

QC Manager _____

R.C. Watson

FAX: (512) 295-2431 [lab] / (512) 295-3102 [accounting]