

Tex Tral

Light Colored Masonry & Stone Cleaner

TEX TRAL is the recommended cleaner for all Spectrum Colored Cements.

TEX TRAL is a cleaner designed specifically for light colored or sensitive colored masonry units and stone. It softens and removes excess mortar and dirt while effectively controlling green vanadium and brown manganese staining on color sensitive tile and brick. It is also safe for most cast or unpolished stone.

APPLICATION PRECAUTIONS: Cover all plants and any other non-masonry item that may be damaged by this product. Beware of drifting of sprayed product, fumes, or rinse water. Avoid exposing anyone without proper safety equipment to spray, splash, or fumes.

APPLICATION: Completely saturate the surface to be cleaned with water. While still wet, apply diluted TEX TRAL to the surface with a dense packed, soft fiber masonry brush or power spray of less than 50 psi. Allow cleaning solution to stay on wall from 1 to 5 minutes, depending on absorption rates and drying conditions. Do not let the cleaner dry on the surface due to the possibility of leaving residue or stains. Rinse thoroughly. Reapply solution if necessary and scrape off buildup of excess mortar. Do not use metal scrapers. Rinse thoroughly with fresh water. Remove all cleaning solution, free sand, loose material, and debris.

READ ALL PRECAUTIONS AND SAFETY INFORMATION BEFORE APPLYING PRODUCT!

HOW TO DILUTE:

- For Brick, limestone natural or man-made, precast, exposed aggregate or tile (glazed or unglazed) mix 5 or 6 parts water to 1 part concentrate. *(Stronger mixes of cleaner to water may be required for extremely stubborn areas, always pretest an inconspicuous area first to avoid staining or damage to the masonry surface.)*
- Very porous sandstone or stone, 7 or 8 parts water to 1 part concentrate.
- For glazed structural tile and ceramic brick, 9 or 10 parts water to 1 part concentrate.

PRETEST ALWAYS! Always test a 3 x 3 foot section to ensure desired results and suitability before overall application. Test each type of stain and each type of masonry.

INTERIOR CLEANING: If rinsing an interior surface is difficult, rinse with clear water, apply a neutralizing rinse of 2 ounces of baking soda to 1 gallon of water and saturate surface with neutralizing solution for 4 to 5 minutes. Finally rinse with clean water.

Houston
2800 N. Gordon St.
Alvin, TX 77511
Ph: (281) 331-0088
Fax: (281) 331-9813
(800) 873-5794

Austin
1585 Jack C. Hays Trail
Buda, TX 78610
Ph: (512) 312-0879
Fax: (512) 295-3277
(800) 499-0984

Dallas
400 N Hwy 377
Roanoke, TX 76262
Ph: (817) 491-0531
Fax: (817) 430-4370
(800) 525-5382